



Installation Details

Overage

Please add a healthy overage ranging 15~20%, as shipping additional material can be expensive.

Fastening (Interior)

Tube adhesive and pin nails

Substrate (Interior)

Per design specification

Installation Layout

Vertical or horizontal, all profiles

Dimensions & Grades Available

Select Grade				
SKU#	Profile	Length	Reveal	SF/pc
SA2551	6" Lap	145 11/16"	5 5/16"	5.33
SB2551	6" S3S	145 11/16"	5 11/16"	5.75
SE2551	8" Lap	145 11/16"	7 5/16"	7.33
SF2551	8" S3S	145 11/16"	7 11/16"	7.75

Prefinish Specifications

Prefinish Option	Interior Grade 3 Coats Polyurethane
Prefinish Color	Black
Exterior Application	No
Interior Application	Yes
Back-Oiling Option	As standard
2nd Coat Oil Option	As standard
Shop-Applied Fire Retardant	Not available
Pressure Treated Fire Retardant	Not available



Manufacturer

Nakamoto Forestry North America

Warehouse and Office (By Appt Only)

6400 SE 101st Ave Unit 2C & 3C
Portland Oregon 97266
Tel. (503) 512-6780

Mailing and Billing

4110 SE Hawthorne Blvd. #190
Portland Oregon 97214

Suyaki Interior with Polyurethane BLACK (previous SKU# NM1686)

Yakisugi "shou sugi ban" paneling. Original unbrushed charred surface, suitable for interior applications. High-traffic, non-toxic, washable surface, with even black color. Delivered ready to install.

Product does not shed soot after installation

Copy and Paste into Appropriate CSI Division

SECTION 06 26 00 or 07 46 00

CHARRED WOOD PANELING

Surface & Texture

Suyaki is a surface with small to large crevasse patterns, variable from 1/4"~1.5" wide rectangles. The soot layer is approximately 1/16" thick.

Species

Cryptomeria japonica, a monotypic genus in the Cypress family native to Japan. The Japanese name is "Sugi" (as in yakisugi and shou sugi ban), and in the West it is colloquially known as "Japanese Cedar".

Wood Grade


JAS "Small Knot" grade allows for up to 20 tight knots per 79" (2m) board length. Unlimited combination of heartwood and sapwood, pith allowed. Checks allowed to 1/16" as long as plank stability, and cosmetics are not adversely affected.

Moisture Content

Air dried then kiln dried to 11~14% MC, but may fluctuate during transport or warehousing. Please acclimate on site for two weeks prior to installation.


1x6 Shiplap Dimensions

- Nominal 1x6x12
- 5 5/16 inches (135mm) actual reveal
- 145 11/16 inches (3700mm) actual length
- 5.33 SF/piece




1x6 Square Edge Dimensions

- Nominal 1x6x12
- 5 5/16 inches (145mm) actual reveal
- 145 11/16 inches (3700mm) actual length
- 5.75 SF/piece




1x8 Shiplap Dimensions

- Nominal 1x8x12
- 7 5/16 inches (185mm) actual reveal
- 145 11/16 inches (3700mm) actual length
- 7.33 SF/piece



1x8 Square Edge Dimensions

- Nominal 1x8x12
- 7 5/16 inches (195mm) actual reveal
- 145 11/16 inches (3700mm) actual length
- 7.75 SF/piece



*Dimensional shrinkage after manufacture is possible due to being a solid-sawn wood product.

