

Gendai Linseed Amber

Yakisugi “shou sugi ban” siding. The top layer of delicate soot has been gently brushed off, leaving a smooth, consistent and dark surface. A natural linseed oil prefinish is applied prior to shipment. Suitable for exterior applications. Available burned both faces for fencing or louver applications. Delivered ready to install.

Copy and Paste into Appropriate CSI Division
SECTION 06 26 00 or 07 46 00
CHARRED WOOD SIDING




**Scan QR code for
pricing, sustainability
and other data**

Profile	Grade	
	Select	Premium Clear
1 x 6 x 12 Shiplap	GA2133	GD2133
1 x 6 x 12 S3S Square Edge	GB2133	–
1 x 6 x 12 S4S Square Edge	GC2133	–
1 x 8 x 12 Shiplap	GE2133	–
1 x 8 x 12 S3S Square Edge	GF2133	–
1 x 2 x 12 S3S Square Edge	–	GG2133
5/4 x 2-1/2 x 12 S3S Square Edge	–	GH2133
5/4 x 2-1/2 x 12 S4S Square Edge	–	GI2133
5/4 x 5 x 12 S3S Square Edge	–	GJ2133
5/4 x 5 x 12 S4S Square Edge	–	GK2133
5/4 x 8 x 12 S3S Square Edge	GL2133	–

Considerations

- Designed to fade and change color over time.
- Opulent light brown living finish.
- Soot residue, caking, and erosion is unavoidable and will cause the finish to blemish, especially along board edges. This is a natural characteristic of this product.


Patina Scale



The Patina Scale has been developed by Nakamoto Forestry to approximate how its products will weather over time—from 0 (“less patina/more color longevity”) to 10 (“less color longevity/more patina”). However, every product weathers at a different rate due to local conditions, and the Patina Scale is intended as general guidance only, and is solely for informational purposes. Nakamoto Forestry makes no guarantees, representations, or warranties, express or implied, regarding the appearance or color longevity of its products after installation.


Wood Grade

Select



JAS “Small Knot” grade allows for up to 20 tight or 10 dead knots per 79” (2m) board length. Unlimited combination of heartwood and sapwood, pith allowed. Checks allowed to 1/16” as long as plank stability, weather-resistance, and cosmetics are not adversely affected.

Premium Clear




Premium Clear grade allows for up to 4 tight or 3 dead pinhole knots per 79” (2m) board length. Unlimited combination of heartwood and sapwood, no face pith allowed. Checks allowed to 1/16” as long as plank stability, weather-resistance, and cosmetics are not adversely affected.

Profiles and Dimensions

(diagrams below are 20% actual size)


1 x 6 x 12 Shiplap

- Charred 3 sides
- 145-11/16"
- (3700mm) length
- 5.33 SF/piece




1 x 6 x 12 S3S & S4S Square Edge

- Charred 3 or 4 sides
- 145-11/16"
- (3700mm) length
- 5.75 SF/piece




1 x 8 x 12 Shiplap

- Charred 3 sides
- 145-11/16"
- (3700mm) length
- 7.33 SF/piece




1 x 8 x 12 S3S Square Edge

- Charred 3 sides
- 145-11/16"
- (3700mm) length
- 7.75 SF/piece




1 x 2 x 12 S3S Square Edge

- Charred 3 sides
- 145-11/16"
- (3700mm) length
- 1.75 SF/piece




5/4 x 2-1/2 x 12 S3S & S4S Square Edge

- Charred 3 or 4 sides
- 145-11/16"
- (3700mm) length
- 2.33 SF/piece




5/4 x 5 x 12 S3S & S4S Square Edge

- Charred 3 or 4 sides
- 145-11/16"
- (3700mm) length
- 4.75 SF/piece



5/4 x 8 x 12 S3S Square Edge

- Charred 3 or 4 sides
- 145-11/16"
- (3700mm) length
- 7.75 SF/piece



*Dimensional shrinkage after manufacture is possible due to being a solid-sawn wood product.

Prefinish

The semi-transparent linseed oil stain is designed to balance raw, natural beauty with color longevity. It absorbs into the wood, conditioning and enhancing the grain. The linseed finish is an excellent choice for owners who want to enjoy the inherent beauty of the wood as it weathers. The siding can be left to patina or re-oiled at any time to freshen up the color.

Prefinish Options

1 coat + back oil: Coated on face and back only

Prefinish Color

Amber

Pressure-Treated Fire Retardant

Not available

Field Cuts

Coat all field cuts and rips with touch up oil

Species

Cryptomeria japonica, a monotypic genus in the cypress family native to Japan. The Japanese name is "sugi", as in yakisugi and "shou sugi ban". In English it is colloquially called Japanese cedar.

Manufacturer

Nakamoto Forestry North America

Warehouse & Office (By Appt Only)

7320 NE 55th Ave.
Portland Oregon 97218
Tel. (503) 512-6780

Installation Details

For installation instructions:

Contact sales@nakamotoforestry.com

Overage

Please add a healthy overage ranging from 15-25%, as shipping additional material can be expensive

Fastening (Exterior)

Two ring or screw-shank headed face nails or screws per furring strip within 1" of each edge

Substrate (Exterior)

Rigid furring maximum 16" on-center

Installation Layout

Vertical or horizontal, all profiles

Fire Resistance

ASTM E2707 & CSFM 12-7A-1 WUI
ASTM E-84

Moisture Content

Air dried then kiln dried to 9-13% MC, but may fluctuate during transport or warehousing. Please acclimate on site for two weeks prior to installation.

